



SINGLE WALL CORRUGATED HDPE PIPE & FITTINGS

APPLICATIONS

- Agricultural Drainage
- Highway Underdrains
- Soil Stabilization
- Retaining Wall Stabilization
- Conduit
- Waste Management
- Residential/Commercial Construction
- Sports Field Drainage

ASTM Standard Material

Pipe shall comply with the test methods, dimensions and markings found in ASTM F405 and F667, along with NRCS Code 606.

AASHTO Standard Material

AASHTO Grade shall comply with test methods, dimensions, and markings found in AASHTO M252 and AASHTO M294.

ASTM & AASHTO grade materials available per job specifications. Available configurations vary. Contact Timewell for details.

AVAILABLE CONFIGURATIONS

Size	Stick Length	Small Coils	Maxi
3"	10'	100'	5600', 6200'
4"	10'	100', 250'	3250'
5"		165'	2300'
6"		100'	1320', 1685'
8"	20'	405'	920'
10"	20'		625'
12"	20'		370'
15"	20'		220'

Nominal Diameter	Inside Diameter (Average)	Outside Diameter (Average)	Minimum Pipe Stiffness at 5% Deflection	Weight (lbs./20ft.)
3"	3.10"	3.60"	35 psi	4.60 lbs
4"	4.05"	4.60"	35 psi	6.85 lbs
5"	5.00"	5.90"	35 psi	10.15 lbs
6"	6.05"	6.90"	35 psi	15.40 lbs
8"	8.15"	9.50"	35 psi	27.40 lbs
10"	10.05"	11.60"	35 psi	40.75 lbs
12"	12.05"	14.20"	35 psi	50.70 lbs
15"	14.95"	17.70"	35 psi	66.10 lbs